DUROSTICK CEILING PAINT



For ceilings



PROPERTIES

Waterborne paint with excellent whiteness and great coverage. Easy to apply, without lap marks, it dries thus it can be repainted quickly. It allows for the breathability of the ceiling, exceptionally useful in areas with concentrated water vapours. In this way, it prevents water vapour accumulation and condensation forming on the ceiling surfaces.

APPLICATIONS

DUROSTICK CEILING PAINT is exceptional for non thermally insulated ceilings, kitchen, baths, bedrooms, etc. Affordable solutions for warehouse and staircase applications. In addition, suitable for freshening already painted surfaces with ceiling paints or glue-paint.

USE

1. Substrate preparation

Surfaces from marble based plaster must be dry and smooth, free from loose materials, oils,

mold, salts, dust, and at least 30 days must have passed from their construction.

For new marble based plaster surfaces, sand using #60 sandpaper or skim with GRANULAR or GRANULAR ULTRA to correct and cover any possible plaster surface defects.

For already painted, sound surfaces, without any cohesion problems, just apply 2-3 coats with DUROSTICK CEILING PAINT.

For surfaces coated with whitewash or gluepaint mixtures, remove any peeling materials or bubbles with sandpaper, putty knife or electric sander.

Surfaces infested with black or green mold or even active fungi, necessarily have to be cleaned using DUROSTICK D-95 CLEANER, rinse thoroughly, dry and prime using SOLVENT BASED PRIMER or the micromolar stabilizer AQUAFIX of DUROSTICK.

2. Application

Dilute DUROSTICK CEILING PAINT with water at a ratio of 5-10%, depending on the substrate, and stir well. Apply with brush, roller or airless

The technical specifications and directions of use contained in this technical brochure are the results of the knowledge and experience of the company's research and development department, as well as from the real-life applications of the product. The recommendations and suggestions regarding the use of the products are made without guarantee since the respective conditions during their application are beyond the control of the company. For this reason, it is the user's responsibility to make sure that the product is suitable for the intended application as well as the application conditions of the project.

DUROSTICK CEILING PAINT



For ceilings

spray gun in 2-3 coats. Apply each additional coat, after the previous one is completely dry.

CLEANING

Clean all tools with water and detergent solution, immediately after use.

PERFORMANCE

Approximately 9-12m²/lt per coat, depending on the texture, the absorbency of the surface and the application method.

STORAGE

Store in places protected from sunlight and frost, for at least 18 months from production date.

SAFETY DIRECTIONS

The product needs no hazard labeling under current European and National legislation. However, it is recommended to keep the product away from the reach of children. If swallowed, seek immediate medical advice and show the container or label.

LIMITATION OF USE

Not recommended to apply on surfaces that are painted with emulsion, acrylic, or enamel paints.

PACKAGING

3lt & 9lt containers

TECHNICAL SPECIFICATIONS	
Color	White that does not yel-
	low over time
Shades	20 basic DU- ROCOLOR liquid pig- ments in 20ml syringe packaging, that create 120 permanent colors.
Gloss	Matte
Drying time	1 hour (touch dry), depending on the ambient conditions
Recoating time	3-4 hours, depending on the ambient conditions
Application	From +8°C to +35°C
temperature	
Flammable	No

V.O.C. (Volatile Organic Compounds): Limit value of maximum V.O.C. content per EC (Directive 2004/42/EC) for the particular product (Class A/a: 'Matte coatings for interior walls and ceilings' Type WB): 30gr/lt (2010). The ready to use product contains maximum 3gr/lt V.O.C

DUROSTICK S.A.

MANUFACTURING OF ADHESIVES, PAINTS & MORTARS ATHENS: ASPROPYRGOS, ATTICA, GR: 193 00, Tel: +30 211 60 03 500-599, +30 210 55 16 500, +30 210 55 98 350. Fax: +30 210 55 99 612

THESSALONIK: INDUSTRIAL PARK-SINDOS, S.B. 44, STREET, DA 0, GR: 570 22, Tel: +30 2310 795 797, +30 2310 797 365, Fax: +30 2310 797 367

Z = 10 / 3/ 300, 1 dx. 130 2310

E-mail: info@durostick.com