

Special Monocottura



Tile adhesive



■ PROPERTIES

Cementitious adhesive for ceramic tiles with low slip. Provides high initial and final adhesive strength, it develops its mechanical strengths rapidly and it is resistant to moisture. Classified C1 per EN 12004 (MIRTEC/Cert. No. 3351).

■ APPLICATIONS

SPECIAL MONOCOTTURA is suitable for interior and exterior wall and floor tile installations. The addition of DUROSTICK ACRYLIC EMULSION in the mixing water, at a ratio of 1:1, improves its technical characteristics, to meet the requirements of C2 class (improved cementitious adhesive) per EN 12004 and S1 class (deformable adhesive), per EN 12002. The improved adhesive then becomes suitable for exterior installations, even for low absorbency tiles.

■ USE

1. Surface preparation

The application surface has to be sound, clean, free of loose materials, dust, paint, grease and oils. The surface has to be soaked before the application.

It is necessary to prime all absorbent substrates and aircrete, using DUROSTICK ACRYLIC EMULSION or D-20, at a mixing ratio of 1:1 with water. It is necessary to prime all cement boards using DUROSTICK micromolar stabilizer, AQUAFIX or SOLVENT BASED PRIMER. Lightweight or else, unstable cement screeds, must necessarily be primed with DUROSTICK ACRYLIC EMULSION or D-20 at a ratio of 1-part additive to 2 parts water or 1-part DUROMAX to 5 parts water. Follow all balcony and terrace applications by coating the substrate with HYDROSTOP FLOOR or D1, with 2-3 successive, crosswise coats to ensure the waterproofing of the substrate.

2. Application

Empty the adhesive into a clean container with cool water at a ratio of 2 parts water to 5.5 parts mortar (6.0-6.5lt water to 25kg mortar or 1.2-1.3lt water to 5kg mortar) and mix with a low rpm electric mixer until a lump free, homogeneous mass is created. Allow the mixture to mature for 5-10 minutes. During use mix periodically, without adding extra water. Apply the adhesive using a notched trowel and

Special Monocottura



Tile adhesive

spread on the substrate. Then, coat as much surface as is required to work for the next 10-20 minutes (depending on weather conditions), thus avoiding skin formation. Finally, install the tiles in the selected position by tapping softly with a rubber mallet.

NOTE

On exterior surfaces, it is highly recommended to create expansion joints every 16-20m². Prime the expansion joints with PRIMER-PU, to improve grip, fill them with the backer rod of DUROSTICK, DS-265, and seal them with the polyurethane sealant, DUROFLEX-PU. Similarly, seal all the joints (5-8mm) at the junction of the tiles and vertical surfaces throughout the perimeter. Alternatively, the application of DS POLYMER sealant, available in 32 colors (same ones with the grout colors of DUROSTICK), ensures sealing without cracking at the junction of the tiles with the skirting and above it as well.

CLEANING

Clean all tools with water, immediately after use.

CONSUMPTION

3-5kg/m², depending on the size of the notch of the trowel, the smoothness of the substrate and the dimensions of the tiles.

STORAGE

- **25kg Paper bag with valve:** For 12 months from production date.
- **5kg Plastic bag:** For 18 months from production date. Store in factory sealed packages, in dry and shaded places.

SAFETY DIRECTIONS

The product contains Portland cement. Before use, refer to the cautions on the product's package or the Material Safety Data Sheet.

PACKAGING

- Carton box with 4 pcs of 5kg each one on a 900kg pallet
- Paper bag of 25kg on 1,500kg pallet.

TECHNICAL SPECIFICATIONS

(Measurement conditions 23°C and 50% R.H.)

Form - Color	Cementitious mortar - White
Bulk density of dry mortar	1.35±0.05kg/lt
Water requirement	6.0lt water per 25kg mortar
Application temperature	From +5°C to +35°C
Temperature resistance	From -20°C to +60°C
Pot life	At least 4 hours
Application thickness	Up to 10mm
Open time per EN 1346	20 minutes
Time for minor adjustments	15 minutes
Grouting	After 4-8 hours on wall, after 24 hours on floor
Foot traffic	After 24 hours
Delivery to use	After 10-14 days

PRODUCT PERFORMANCES

Adhesion strength, per EN 1348, after:

• 28 days	1.20 N/mm ²
• Thermal ageing at +70°C	0.90 N/mm ²
• Water immersion for 21 days	0.90 N/mm ²
• 25 freeze - thaw cycles	0.95 N/mm ²

The experimental measurements were performed per EN 12004, in the Chemical Laboratory of DUROSTICK and were confirmed by the measurements of initial type from MIRTEC (Cert. No. 3351).

NOTE: The product exceeds the statutory requirements for C1 adhesive.

Special Monocottura



Tile adhesive

CE	
DUROSTICK S.A. ASPROPYRGOS ATHENS PC:193 00 GREECE 07	
DoP No.: 001 EN 12004:2007 + A1:2012	
SPECIAL MONOCOTTURA Normal setting cementitious adhesive. Internal wall and floor tiling.	
- Reaction to fire:	Euroclass A1
- Release of dangerous substances:	see MSDS
Bond Strength as:	
- Initial tensile adhesion strength:	≥ 0.50N/mm ²
Durability of bond expressed as:	
- Tensile adhesion strength after heat ageing:	≥ 0.50N/mm ²
- Tensile adhesion strength after water immersion:	≥ 0.50N/mm ²
- Tensile adhesion strength after freeze-thaw cycles:	≥ 0.50N/mm ²

DUROSTICK S.A.,
MANUFACTURING OF ADHESIVES,
PAINTS & MORTARS
ATHENS: ASPROPYRGOS, ATTICA, GR: 193 00,
Tel: +30 211 60 03 500-599, +30 210 55 16 500,
+30 210 55 98 350, Fax: +30 210 55 99 612
THESSALONIKI: INDUSTRIAL PARK-SINDOS, S.B. 44,
STREET, DA 10, GR: 570 22,
Tel: +30 2310 795 797, +30 2310 797 365,
Fax: +30 2310 797 367
Email: info@durostick.com