

VITREOUS TILE & MARBLE GROUT



Ultrafine 0-3mm



PROPERTIES

Cementitious colored grout with selected quartz aggregates, reinforced with special acrylic polymer resins. The resulting finish surface of the grout is vitreous/porcelain-like and water repelling, while it does not allow for the accumulation of dirt and bacteria. It applies easily and cleans rapidly, presenting exceptional color stability and uniformity. It is resistant to both moisture and abrasion.

Classified CG2/WAr per EN 13888.

APPLICATIONS

Suitable for grouting widths from 0-3mm, both indoors and out, wall and floor surfaces lined with ceramic tiles, marble, polished and honed granite, glass mosaic, as well as wherever the aesthetics of the space or lining requires ultra smooth joints.

USE

Surface preparation

Remove from the tile surface all adhesive residues and clean the grout joints with a damp

sponge. For exterior surfaces, the creation of expansion joints every 16-20m² is recommended. Prime the joints using PRIMER-PU and install the backer rod DS-265. After 2-3 hours, apply the elastomeric polyurethane sealant DUROFLEX-PU to fill the joints. Also the creation of perimeter expansion joints, 5-8mm wide, both indoors and out, is strongly recommended. Create expansion joints between the tiles and vertical surfaces, and fill in the same way as described above, thus reducing the compression of the joints from expansions and contractions. Alternatively, apply DS POLYMER, available in 32 colors (same with the grout colors of DUROSTICK), to ensure sealing without cracking at the junction of the tiles with the skirting and above it as well. For interior floors with radiant heating systems, it is recommended to create expansion joints every 20m². The use of DS POLYMER, available in 32 colors, will prevent the appearance of hairline cracks on the surface of the grouting material, and the consequent detachment of tiles

VITREOUS TILE & MARBLE GROUT



Ultrafine 0-3mm

Application:

Empty the mortar into a clean container with cool water, at a ratio of 1.5-1.6lt water to 5kg mortar, and mix with a low-rpm drill, until a lump free, homogeneous mass is created. Allow the mixture to mature for 5-10 minutes and mix periodically, without adding extra water. Apply the grout using a grouting float, working diagonally towards the grout joints, without leaving any gaps or residues. When the grout begins to set, remove the residues using a damp sponge. Finally, when the material completely cures, clean/shine the surface with a dry cotton cloth. The addition of DUROSTICK ACRYLIC EMULSION in the mixing water, at a ratio of two parts water to one part emulsion, increases its impermeability and resistance to temperature variations (balconies, terraces, radiant heating). If a higher degree of flexibility is required, then use the FLEXIBLE & OIL REPELLENT grout of DUROSTICK, for tiles and marble. For spaces highly resilient to strict hygiene requirements, the use of the epoxy grout DUROPOXY of DUROSTICK is highly recommended..

NOTES

- Avoid grouting at temperatures above 35°C when the surface is exposed to sunlight thus preventing cracking. If this is unavoidable, cover with wet burlap or polystyrene panels the still wet grouted surface.
- It is recommended to clean any grout residues using the DUROSTICK ACID TILE CLEANER, but only after 20 days have passed from the grouting of the surface.

CLEANING

Clean all tools with water, immediately after use.

HELPFUL TIP

DUROSTICK grouts are available in a variety of colors able to meet every styling requirement in relation with the lining. Furthermore, it is possible to color the DUROSTICK grouts, using the DUROCOLOR POWDER-C system. Color the white grouts based on the existing color chart or experiment creating unique colors or shading combinations.

CONSUMPTION

The following table is the indicative consumption, depending on the width and the depth of the joint, as well as the dimensions of the tiles.

JOINT WIDTH (mm)				JOINT WIDTH (mm)
TILE DIMENSION S (cm)	1	2	3	
2 x 2 x 0,38 (mosaic)	400	800	1200	
10 x 10 x 0,60	160	320	480	
15 x 15 x 0,70	125	250	375	
20 x 20 x 0,70	90	180	270	
30 x 30 x 1	80	160	240	

The consumption rates refer to gr/m²

STORAGE

Store in factory sealed packages, in dry and shaded places, for at least 18 months from production date.

PACKAGING

Carton box with 4 pcs. of 5kg each one, on 720kg pallet.

VITREOUS TILE & MARBLE GROUT



Ultrafine 0-3mm

Strength after 28 days, per EN 12808-3, in	
Flexion	6.00±0.80 N/mm ²
Compression	40.00±1.50 N/mm ²
Strength after 25 freeze-thaw cycles, per EN 12808-3, in	
Flexion	5.00±0.80 N/mm ² ,
Compression	40.00±1.50 N/mm ²
Shrinkage per EN 12808-4:	≤1 mm/m
Abrasion resistance per EN	≤1.000 mm ³
Water absorption per EN 12808-5	
after 30 minutes	≤ 2 gr
after 240 minutes	≤5 gr

TECHNICAL SPECIFICATIONS (Measurement conditions: 23°C and 50% R.H.)	
Form	Cementitious mortar
Color	5 permanent colors. The white grout can be colored for additional choices.
Toxic	No
Bulk density of dry mortar	1.05±0.05kg/lt
Bulk density of fresh mortar	1.65±0.05kg/lt
Water requirement	1.5 to 1.6lt water to 5kg mortar, depending on the color
Application temperature	From +5°C to +35°C
Temperature resistance	From -30°C to +80°C
Pot life	3 hours
Grouting time after tile installation	4-8 hours on walls, 24 hours on floors, 2-3 hours for fast setting adhesive on floors, 1 hour for fast setting adhesive on walls
Foot traffic	After 8 hours
Acid resistance	Excellent when pH > 3 (thinned).
PRODUCT PERFORMANCES	

The technical specifications and directions of use contained in this technical brochure are the results of the knowledge and experience of the company's research and development department, as well as from the real-life applications of the product. The recommendations and suggestions regarding the use of the products are made without guarantee since the respective conditions during their application are beyond the control of the company. For this reason, it is the user's responsibility to make sure that the product is suitable for the intended application as well as the application conditions of the project.

VITREOUS TILE & MARBLE GROUT



Ultrafine 0-3mm

DUROSTICK S.A.

MANUFACTURING OF ADHESIVES, PAINTS
& MORTARS

ATHENS: ASPROPYRGOS, ATTICA, GR: 193 00, Tel:
+30 211 60 03 500-599, +30 210 55 16 500, +30 210 55
98 350, Fax: +30 210 55 99 612

THESSALONIKI: INDUSTRIAL PARK-SINDOS, S.B. 44,
STREET, DA 10, GR: 570 22, Tel: +30 2310 795 797, +30
2310 797 365, Fax: +30 2310 797 367

E-mail: info@durostick.com